

| | | | | | |
|--------------------------|-----------------------------------|-------------------|-----------------|---------------|------------|
| Beamline | PF BL-16A | | | | |
| Sample | BN (powder on carbon tape) | | | | |
| Edge | N-K | | | | |
| Method | Total electron yield | | | | |
| Date | 2018.6.19 | | | | |
| Data block | XANES range = 380 - 460 | | | | |
| | | Energy /eV | Step /eV | Num | |
| | 1 | 380 | 400 | 1 | 20 |
| | 2 | 400 | 410 | 0.1 | 100 |
| | 3 | 410 | 425 | 0.2 | 75 |
| 4 | 425 | 460 | 1 | 35 | |
| Total data points | | | | 230 | |
| Measure time | | | | 21 min | |

