

Beamline	PF BL-7A				
Sample	NiO (powder on carbon tape)				
Edge	O-K				
Method	Total electron yield				
Date	2018.2.18				
Data block	XANES range = 510 - 550				
		Energy /eV	Step /eV	Num	
	1	510	525	1	15
	2	525	535	0.1	100
	3	535	550	0.2	75
4	550	630	1	80	
Total data points				270	
Measure time				5 min	

