

Beamline	PF BL-16A				
Sample	TiO₂ (powder on carbon tape)				
Edge	Ti-L				
Method	Total electron yield				
Date	2018.6.19				
Data block	XANES range = 440 - 525				
		Energy /eV	Step /eV	Num	
	1	440	455	1	15
	2	455	470	0.05	300
3	470	525	1	55	
Total data points				370	
Measure time				35 min	

